

STRATLOCK SL RANGE

SL-SFA & SL-SFA-FR PRODUCT GUIDE


SL-SFA Stratlock® Female Side Mount – For Timber

SL-SFA-FR Stratlock® Female Side Mount - Fire-rated

The SL-SFA provides rapid installation of heavy panels to timber, steel or aluminum framework. Designed specifically for contract interior fitout applications to reduce onsite installation time. Female installs onto side of framework with 2 x #8 panhead screws (1/4") in timber frames, and #8 tek screws (1/4") into steel or aluminum framework. Used with the SL-M10/SL-M18 / SL-M18-FR the new solid internal load chassis creates 5/32" supported movement of the panel in any direction at the first engagement before locking into place with an 10/39.6lb pull out load. The distance between the panel and substrate when installed is 1/2" at the first click, and 0.24" when pressed into final position. Patent Pending.


SL-SFA

SL-SFA-FR



USE WITH:

SL-M10, SL-M18, SL-M18-FR



MATERIAL:

White Acetal copolymer/Rubber ring
Off white FR Nylon/Rubber ring

MORE INFO:

Installation Guide SL-SFA
Clip Layout Guide TD-15, 17
Panel Offset Guide


BENEFITS

- Strongest mounting available
- Side mount with rapid screw fixing
- Supported movement of the panel 5/32" in any direction before locking into final position.
- No special tools required for installation
- Acoustic isolation between panel and frame
- Option of 22lb or 39.6lb pull out load with SL-M10 or SL-M18
- 0.24" clearance between panel and frame
- SL-SFA-FR available in V-0 rated FR nylon

APPLICATIONS

- Commercial interior fitout
- Residential interior fitout
- Architectural applications
- Mounting heavy wall panels
- Fire-rated interior panels

INSTALLATION: Partially exploded through section showing typical installation method



STRATLOCK SL RANGE

SL-SFA & SL-SFA-FR PRODUCT GUIDE

Below are the associated certifications for the above-mentioned Fire Rated materials used in the SL-SFA-FR:

UL-Yellow card for Grilon AS V0

UL-Yellow card for Technyl B50H1

Component - Plastics

E132701

EMS-CHEMIE (TAIWAN) LTD

36 KWANG FU SOUTH RD, HSIN CHU INDUSTRIAL PARK, FU KOU HSIANG, HSIN CHU HSIEN
30351 TW

Grilon AS V0

Polyamide 66 (PA66), unreinforced, "Grilon", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	0.75	V-0	4	0	115	105	120
	0.85	V-0	4	0	115	105	120
	1.5	V-0	2	0	115	105	120
	3.0	V-0	1	0	115	105	120

Comparative Tracking Index (CTI): 0

Dielectric Strength (kV/mm): -

High-Voltage Arc Tracking Rate
(HVTR): 0

Dimensional Stability (%): -

Inclined Plane Tracking (IPT): -

Volume Resistivity (10^x ohm-cm): -

High Volt, Low Current Arc Resis
(D495): 5

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1990-07-09

Last Revised: 2009-12-03

© 2011 Underwriters Laboratories Inc.



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.75	V-0 (ALL)
			0.85	V-0 (ALL)
			1.5	V-0 (ALL)
			3.0	V-0 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	0.85	960
			1.5	960
			3.0	960
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2011 Underwriters Laboratories Inc.

STRATLOCK SL RANGE

SL-SFA & SL-SFA-FR PRODUCT GUIDE

Component - Plastics

E507491

Guide Information

BASF Engineering Plastics (Shanghai) Co., Ltd.

3966 JIN DU RD, XIN ZHUANG INDUSTRIAL ZONE, SHANGHAI 201108 CN

B 50H1(r1)(f2)

Polyamide 66/6 (PA66/6), unfilled "Technyl or Ultramid", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	0.38	V-0	4	0	120	-	-
	0.75	V-0	4	0	120	90	95
BK	1.0	V-0, 5VB	4	0	120	90	95
ALL	1.5	V-0	4	0	120	90	95
	3.0	V-0	3	0	120	90	95

Comparative Tracking Index (CTI): 0

Dielectric Strength (kV/mm):

High-Voltage Arc Tracking Rate (HVTR): 0

Dimensional Stability (%): -

Inclined Plane Tracking (IPT) kV: -

Volume Resistivity (10^x ohm-cm):Surface Resistivity (10^x ohms/square):

High Volt, Low Current Arc Resis (D495): 6

(f2) - Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL

(r1) - Virgin and regrind up to 50% by weight incl. have the same basic material characteristics, except for the 5VB rating.

NOTE - Materials designated "Technyl" may be prefixed by the letters "TY".

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL

Report Date: 1993-10-21

Last Revised: 2020-05-07

© 2020 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	0.38	V-0 (ALL)
			0.75	V-0 (ALL)
			1.0	V-0, 5VB (BK)